

# CIKOflow WP

Smart Chemical Solutions



## Waterproofing admixture for concrete and mortar

### Description

CIKOflow WP is a capillary or pore reducing concrete admixture that minimizes the permeability of concrete mix. It is suitable for both plain and structural concrete.

The active ingredients in CIKOflow WP disperses the cement evenly in the mix reducing the water-cement ratio and thereby reduction in permeability

### Properties

- Minimise porosity and permeability in the concrete.
- Suitable for all kinds of concrete.
- Uniform distribution throughout concrete mix.
- Provides durable concrete or mortar.

### Application area

- All water retaining structure such as water tanks and swimming pools.
- Structural elements such as roof slab, retaining walls and basements.
- More suitable for tunnels and coastal structures.
- Concrete subjected to immersed conditions.
- Damp-proof screeds for bathrooms and kitchens.

### Applicable standards

CIKOflow N complies with BS EN 934-2 Table 9.

### Physical Properties

Form	Liquid
Colour	Dark brown
Specific Gravity	1.165±0.02 at 25 °C
Chloride Content	Nil to BS 5075
Compatibility	Compatible with other CIKO admixtures and all types of cement

### Dosage

The normal dosage is 1.0 litre per 100kg cement should be added to the concrete.

The optimum dosage should be determined by conducting laboratory/site trials considering proposed mix design, ambient conditions and performance requirements. To achieve good workability, it is advisable to use CIKO range of water reducing admixture in conjunction with CIKOflow WP.

### Usage instructions

CIKOflow WP is a ready to use concrete admixture. Required/calculated amount of CIKOflow WP should be measured by means of measuring jar or dispenser and should be added to concrete / mortar during mixing process preferably at the same time along with water.

In case of dual admixture usage, the water reducing admixture should be dosed first into concrete and mixed for 2-3 minutes followed by the dosing of CIKOflow WP.

To attain optimum efficiency of the admixture, it is always recommended to dose CIKOflow WP to wet concrete / mortar mix. This can be done by mixing 70-75% of the total water with all other ingredients of concrete / mortar followed by the addition of CIKOflow WP diluted with remaining 25-30% water.

### Compatibility with other admixtures

CIKOflow WP is compatible with other CIKO admixtures provided each admixture is dispensed separately into the concrete. Site trials should be conducted to obtain optimum dosage. Contact CIKO technical service department for any further information.

### Packaging

CIKOflow WP is available in 20 litre pails and 200 litre drums.

### Shelf Life

CIKOflow WP has a minimum shelf life of 12 months if stored in accordance with CIKO instructions.

## Storage

CIKOflow WP should be stored under enclosed shaded area.

## Precautions

- Dosage shall not be more than the maximum limit

### *Effect of over dosage:*

Over dosage to the extent of double the recommended dosage of CIKOflow WP will lead to excess air entrainment and reduction in compressive strength of concrete.

## Health & Safety

CIKOflow W should not come in contact with eyes or to be swallowed. If comes in contact with eyes, flush with plenty of fresh water and seek medical advice.

CIKOflow W is water based material and non-flammable.

Refer Material Safety Data Sheet for further details.

## **Technical Support**

*For any technical support, do not hesitate to contact CIKO team at any time as CIKO offers on and off site services to end users, specifier and contractors.*

## **More from CIKO Middle East**

A wide range of construction chemical products are manufactured by CIKO Middle East which includes:

- Concrete admixtures and additives
- Waterproofing and damp proof coatings
- Surface treatments
- Flooring and toppings
- Grouts and anchors
- Tile adhesives and grout
- Concrete repair materials
- Adhesives and bonding agent
- Protective coating
- Joint Sealants and Moulding compounds
- Ancillaries

TDS/AD18 Rev.:1 Issue:C

Note: The information presented herein based on the best of our knowledge and expertise for which every effort is made to ensure its reliability. Although all the products are subjected to rigid quality tests and are guaranteed against defective materials and manufacture, no specific guarantee can be extended because results depend not only on quality but also on other factors beyond our control

