

CIKOjoint PU50



Two components Polyurethane based joint and calk sealant

Description

CIKOjoint PU50 is two-components polyurethane based joint sealant for horizontal and vertical applications for expansion and contraction joints as well as for calking and glazing in buildings and other structures. The cured material provides highly elastomeric property which exhibits a total movement accommodation of 25%.

CIKOjoint PU50 base is polyurethane resin reinforced with suitable agents cured with special hardener and extenders to form an elastomeric solid seal capable of resistance against water, wind and dirt.

Advantages & Properties

- Cold applied two components system.
- Available in both types self-levelling (pouring grade) and Non-sag (gun grade) consistency.
- Durable, Accommodates compression-extension cyclic movement of plus minus 25% of the nominal half joint width.
- Exhibits good UV resistance.
- Provides excellent bond strength over a wide range of porous and non-porous substrates.
- Good chemical resistance against mild acids, hydroxides, and hydrocarbons.
- Available in wide range of colours.

Application Area & Uses

CIKOjoint PU50 is a high-quality joint and calk sealant suitable for several areas of use such as:

- Expansion and contraction joints in buildings and structures.
- Concrete pre-cast claddings and panels.
- Industrial floors and basements.
- Joints on roofs, glazing and calking applications.
- Joints in pedestrian and vehicular traffic areas such as walkways, plazas, decks and parking garages.

Applicable Standards

CIKOjoint PU50 complies with minimum performance requirements of:

- ASTM C-920 Type M, Grade NS & P, use T₁, Class 25
- TT-S-00227E, Type I and II, class B.

Physical Properties

Form and Rheology	Viscous liquid or thixotropic/non sagging paste
Tack free time	36-48 hours @ 25±2°C (GG and PG)
Initial Curing time	72 hours @ 25±2°C (GG and PG)
	48 hours @ 35±2°C (GG and PG)
Final cure	7 days @ 25±2°C (GG and PG)
	5 days @ 35±2°C (GG and PG)
Pot life/working time	25-35 minutes @ 25±2°C (GG)
	20-40 minutes @ 25±2°C (PG)
Solid content (ASTM D2369)	98-100%
Permanent Service temperature	-20°C up to 70°C
Width to depth ratio (W/D)	1:1 for joint width ranging from 5 up to 10mm
	2:1 for joint width ranging from 10 mm up to 50 mm
Colours	Grey. Other colours depend upon request.
VOC (USEPA-24)	<50 g/L

Application Instructions


Surface preparation

Clean the joint substrate to make it free from all loose particles, dust, oil grease and any other form of contamination that might prevent adhesion. In case of oil spillage, proper chemical and mechanical treatment should be carried out to the surface. The joint must be dry, clean, free from dampness and standing water. Glass, stainless steel, aluminium and other metals must be degreased with alcohol based or MEK based solvents.

Placing backup rod and masking tape

Use closed cell polyethylene profiles, maintain a straight joint with proper edges that can receive a sealant having width to depth ratio of 1:1 or 2:1 depending on joint width.

The depth of the sealant shall be maintained by properly placing the backup rod. Fix masking tape on upper face of the concrete or substrate.



Primer Application

Primer is not required, however for porous surfaces such as concrete and other alkaline surfaces prime using CIKOprimer PU. Apply the primer on the sides of the clean, dry joints using brush. Allow the primer to become tacky before applying joint sealant CIKOjoint PU50.

Mixing

The base component of CIKOjoint PU50 should be mixed thoroughly using a heavy-duty slow speed drill fitted with paddle and ensure a homogenous mix. Then hardener component should be poured totally into the base component and mixed well for minimum 2 minutes until a homogenous mix is obtained.

Application method

Horizontal Joints – Pouring Grade

Properly mixed material can be directly poured into the primed joint and levelled to the surface of concrete. To remove bubbles generated during pouring, gently swipe the surface by using a thin flexible pad after 20-30 minutes of application.

Vertical Joints – Gun Grade

Properly mixed material shall be first filled inside sealant gun or filled using a putty knife or suitable tool, then the joints must be filled by triggering required amount sealant. The surface shall be levelled using spatula. Remove the masking tape gently.

Packaging

CIKOjoint PU50 is available in 2.5 ltr [Gun Grade] and 4.0 ltr [Pouring Grade] kits.

Storage

CIKOjoint PU50 should be stored under enclosed shaded area at temperatures between 5°C and 25°C away from direct sunlight, freeze, moisture and flammable materials.

Legal Notice and Warranty

CIKO warrants this product to be free from manufacturing defects and to meet the technical properties stated in the current Technical Data Sheet, if used as directed within its shelf life. Satisfactory results depend not only on quality of product but also on many factors beyond our control. CIKO makes no other warranty or guarantee, express or implied, including warranties of merchantability or fitness for a particular purpose with respect to its product. The sole and exclusive remedy of purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of CIKO. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by purchaser. CIKO will not be responsible for any special incidental, consequential including lost profits or punitive damages of any kind. Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on CIKO's present knowledge and experience. However, CIKO assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. CIKO reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified experts.

TDS/JS24 Rev.: 4 Issue: C

All CIKO products are manufactured under a strict management system conforming to and in compliance with requirements of international standards of Quality, Environmental, occupational Health and Safety ISO 9001, ISO14001 and ISO45001.

Shelf life

CIKOjoint PU50 has a shelf life of 6 months in unopened pails and if stored in accordance with manufacturer instructions.

Precautions

- Do not use over damp surface or standing water.
- The product is highly moisture tolerant, do not apply in conditions where relative humidity is recorded above 75%.
- Protect the applied sealant from any source of water, condensate, disturbance for at least 36 hours.
- Recommended ambient and substrate temperature during application is 5°C up to 40°C

Health & safety

CIKOjoint PU50 should not come in contact with eyes or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Applicator should wear appropriate clothes, gloves and goggles. Use of barrier cream is recommended to provide additional skin protection. If comes in contact with eyes, flush with plenty of fresh water and seek medical advice. Refer Material Safety Data Sheet for further details.

Technical Support

For further technical support, do not hesitate to contact CIKO team at any time as CIKO offers on and offsite services to end users, specifier and contractors.

More from CIKO Middle East

A wide range of construction chemical products are manufactured by CIKO Middle East which includes:

- Concrete admixtures and additives
- Waterproof and Damp-proof coatings
- Surface Treatments
- Walls, Flooring and Toppings
- Grouts and anchors
- Tile Adhesives and Grouts
- Concrete Repair Materials
- Adhesives and Bonding Agents
- Protective Coatings & Sealers
- Joint Sealants and Moulding compounds
- Sports Flooring
- Plastering Mortars
- Paints