سيخوالشرق الأوسط CIKOpoxy Floor SL1000 CIKO مسيكو الشرق الأوسط MIDDLE EAST

Epoxy based, solvent-free self-levelling floor-top system

Description

CIKOpoxy Floor SL1000 is a solvent-free epoxy self-levelling multi component floor-top system recommended for concrete and other suitable substrates.

CIKOpoxy Floor SL1000 is based on liquid epoxy resin cured with a special grade of hardener. It offers seamless floor having a thickness of 0.8 to 2 mm. It provides a smooth, hygienic floor with excellent chemical resistance.

Advantages & Properties

- Flowable consistency for self-levelling application.
- Pre-weight multi component epoxy-based system
- Easy to apply
- Exhibits good wear and abrasion resistance
- Seamless finish; easy to clean and maintain hygienic.
- Anti-bacterial: it will not support the growth of bacteria.
- Resistance to general chemicals
- Excellent durability and impact resistance

Application Area & Uses

CIKOpoxy Floor SL1000 as floor topping is suitable to use both in industrial and commercial segments such as,

- Hospitals and laboratories.
- Warehouse floors and food storage areas.
- Kitchens
- Utility services building floors.
- Pharmaceutical industries.
- Light engineering work shops.
- Walkways and loading bays.
- Production and storage areas.
- · Electricity substation floors.

Coverage

CIKOpoxy Floor SL1000 will provide coverage of 12-13m2 per pack of 20 kg at 1mm dry film thickness. Note: The coverage depends on the floor condition and finish. Consult CIKO technical service department for assistance.

Physical properties

ColourStandard coloursMixing ratioPre weighed packsPot life @25 °C>60 minutesSurface dry3-4 hoursTack freeApprox. 8 hoursFoot traffic18-24 hoursFinal cure7 daysCompressive strength ASTM C109 @ 7 days>65 MPaTensile Strength ASTM D638 @ 7 days>10 MPaPull off Bond Strength ASTM D7234>2.5 MPaShore A hardness ASTM D224085±5	Form	3 component system Part-A & B: Liquid Part-C: Powder
Pot life @25 °C >60 minutes Surface dry 3-4 hours Tack free Approx. 8 hours Foot traffic 18-24 hours Final cure 7 days Compressive strength ASTM C109 @ 7 days Tensile Strength ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 >60 minutes >65 MPa >65 MPa >10 MPa >2.5 MPa >2.5 MPa	Colour	Standard colours
Surface dry Tack free Approx. 8 hours Foot traffic 18-24 hours Final cure 7 days Compressive strength ASTM C109 @ 7 days Tensile Strength ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 3-4 hours 7 days >65 MPa >10 MPa >2.5 MPa 85±5	Mixing ratio	Pre weighed packs
Tack free Approx. 8 hours Foot traffic 18-24 hours Final cure 7 days Compressive strength ASTM C109 @ 7 days Tensile Strength ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 Approx. 8 hours 7 days >65 MPa >10 MPa >2.5 MPa 85±5	Pot life @25 °C	>60 minutes
Foot traffic 18-24 hours Final cure 7 days Compressive strength ASTM C109 @ 7 days Tensile Strength ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 Shore Strength S5±5	Surface dry	3-4 hours
Final cure 7 days Compressive strength ASTM C109 @ 7 days Tensile Strength ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 Final cure 7 days >65 MPa >10 MPa >2.5 MPa >2.5 MPa S1 MPa >2.5 MPa S1 M	Tack free	Approx. 8 hours
Compressive strength ASTM C109 @ 7 days Tensile Strength ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 >65 MPa >10 MPa >2.5 MPa 85±5	Foot traffic	18-24 hours
ASTM C109 @ 7 days Tensile Strength ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 >05 MPa >10 MPa >2.5 MPa 85±5	Final cure	7 days
ASTM D638 @ 7 days Pull off Bond Strength ASTM D7234 Shore A hardness ASTM D2240 >10 MPa >2.5 MPa 85±5		>65 MPa
ASTM D7234 Shore A hardness ASTM D2240 85±5		>10 MPa
ASTM D2240 85±5		>2.5 MPa
VOC. <10a/l		85±5
10g/1	VOC	<10g/l

Chemical Resistance

CIKOpoxy Floor SL1000 is resistant to a wide range of chemicals. Specific data is available on request.

Application instructions Surface preparation

The concrete surface should be free from dust and loose particles. All contamination such as oil, grease and extraneous spillages must be cleaned using the suitable cleaning agent. Concrete shall be grinded, grit blasted or treated with equivalent and suitable mechanical means prior to the application of the primer.

Priming

CIKOpoxy Prim 11 or 14, a two-component epoxy-based primer shall be used for priming the substrate. The base [Part-A] and hardener [Part-B] components of CIKOpoxy Prim11 should be mixed thoroughly using a heavy duty, slow speed drill paddle assembly for three to five minutes and ensure a homogenous mix is obtained. Application of primer should be carried out as per the respective technical data sheet. Allow the primer to dry for 12 -24 hours depending on the prevailing ambient conditions.



Application of self-levelling material

The base component [Part-A] of CIKOpoxy Floor SL1000 should be mixed thoroughly using a heavy-duty slow speed drill-paddle assembly for two minutes and ensure that a homogenous mix with uniform colour is obtained. Transfer the mixed base component [Part-A] completely to a suitable container that can hold a volume of minimum 20 lts.

Pour the hardener component [Part-B] into the mixed base component [Part-A] and mix well to homogeneity. Add the powder component Part-C to the properly mixed Part-A & Part-B and mix well to obtain a homogenous mass.

Properly mixed materials should be spread over the dry and clean primed surface using a notched trowel maintaining the required thickness. Immediately spike the applied surface using spike rollers to release entrapped air in the material to obtain a uniform, smooth and even finish. The coated surface should be left for 12 - 24 hours curing, depending on the prevailing ambient conditions.

Precautions

Prior application of primer and CIKOpoxy Floor SL1000, ensure that:

- Moisture content of the substrate is less than 4%.
- Ambient temperature is between $10 45^{\circ}$ C.
- Substrate temperature is between 10 40°C.
- Relative humidity is below 75%.
- Substrate temperature is at least 30°C greater than the dew point temperature.

Packaging

CIKOpoxy Floor SL1000 is available in 20 kg packs consisting of Part-A, B & C.

Storage

CIKOpoxy Floor SL1000 should be stored under enclosed shaded area at temperatures between 5°C -35°C.

Shelf life

CIKOpoxy Floor SL1000 has a shelf life of 12 months if stored in accordance with CIKO instructions.

Health & safety

CIKOpoxy Floor SL1000 should not come in contact with eyes or be swallowed. Ensure adequate ventilation and avoid inhalation of vapours. Applicator should wear appropriate clothes, gloves and goggles. Use of barrier cream is recommended to provide additional skin protection. If comes in contact with eyes, flush with plenty of fresh water and seek medical advice. Refer Material Safety Data Sheet for further details.

Technical Support

For further technical support, do not hesitate to contact CIKO team at any time as CIKO offers on and off-site services to end users, specifier and contractors.

More from CIKO Middle East

A wide range of construction chemical products are manufactured by CIKO Middle East which includes:

- Concrete admixtures and additives
- Waterproof and Damp-proof coatings
- Surface Treatments
- Walls, Flooring and Toppings
- Grouts and anchors
- Tile Adhesives and Grouts
- Concrete Repair Materials
- Adhesives and Bonding Agents
- Protective Coatings & Sealers
- Joint Sealants and Moulding compounds
- Sports Flooring
- Plastering Mortars
- **Paints**

Legal Notice and Warranty

CIKO warrants this product to be free from manufacturing defects and to meet the technical properties stated in the current Technical Data Sheet, if used as directed within its shelf life. Satisfactory results depend not only on quality of product but also on many factors beyond our control. CIKO makes no other warranty or guarantee, express or implied, including warranties of merchantability or fitness for a particular purpose with respect to its product. The sole and exclusive remedy of purchaser for any claim concerning this product, including but not limited to, claims alleging breach of warranty, negligence, strict liability or otherwise, is the replacement of product or refund of the purchase price, at the sole option of CIKO. Any claims concerning this product must be received in writing within one (1) year from the date of shipment and any claims not presented within that period are waived by purchaser. CIKO will not be responsible for any special incidental, consequential including lost profits or punitive damages of any kind. Purchaser must determine the suitability of the products for the intended use and assumes all risks and liabilities in connection therewith. This information and all further technical advice are based on CIKO's present knowledge and experience. However, CIKO assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third-party intellectual property rights, especially patent rights, nor shall any legal relationship be created by or arise from the provision of such information and advice. CIKO reserves the right to make any changes according to technological progress or further developments. The Purchaser of the Product(s) must test the product(s) for suitability for the intended application and purpose before proceeding with a full application of the product(s). Performance of the product described herein should be verified by testing and carried out by qualified expert.











